

Artículo/Article		MICROFIBRA 86 TECNOSANI		TEST ITEL CE-11343	
REUSABLE (>25 washes)		MADE IN SPAIN		TESTED (ACCORDING UNE-EN14683 and UNE-0065 CEE/93/42 ACABADO HIDROFUGADO Y ANTIBACTERIANO)	
ANÁLISIS FÍSICO / PHYSICAL ANALYSIS					
CARACTERÍSTICAS		RESULTADOS / RESULTS		VALORES / VALUES	
TEST					
Nº de Hilo/Thread Count	Urdimbre / Warp		75D		
	Trama / Weft		150D		
Densidad / Density	Urdimbre / Warp		104		
	Trama / Weft		71		
Ligamento / Weave		PLANA / PLAIN			
Comp. Urd./ Comp. Warp		100% PES GRS POST CONSUME		ISO 1833:2006	
Comp. Tr./ Comp.Weft		100% PES			
Total Comp.		51% PES GRS POST CONSUME - 50% PES		Simple: No tolerancia Compuesta: +/- 3%	
Ancho Final / Final Width		cm	160 - 165		+/-2%
Peso / Weight		gr/m ²	82 - 86		+/-5%
Resistencia Rotura/ Breakage	(Kgs.)	Urdimbre		pass	kgf
		Trama		pass	kgf
Resistencia Abrasion		pass		EN-13795	
Resistencia Desgarro / Tear		Urdimbre/Warp (G)	N/A	Trama / Weft	N/A
Encogimiento / Shrinkage		°C	60	% Urdimbre +/- 2 % Trama +/- 2	0 - 3 % NP EN ISO 5077:2008
SPECIAL MEDICAL TESTS					
CARACTERÍSTICAS		RESULTADOS / RESULTS		VALORES / VALUES	
TEST					
Washing solidity 60°C		4,5		0-5	
Pilling		5		0-5	
Traspirability		< 60 Pa/cm ²		AST1	
Aerosol Filtration Efficiency		>95%		UNE EN 14683	
Particle Filtration Efficiency		>94%		UNE EN 14683	
Particle Filtration		0,3 micras and >95% efficiency		UNE EN149	
Bacterial presence		DRY: PASS	WET: PASS	EN-13795	
ANÁLISIS QUÍMICO / CHEMICAL ANALYSIS					
CARACTERÍSTICAS		RESULTADOS / RESULTS		VALORES / VALUES	
TEST					
pH		Conforme/According Oeko-Tex II		4,0 - 7,5	
Formaldehído		Conforme/According Oeko-Tex II		<16ppm	<75ppm
Arlaminas		Conforme/According Oeko-Tex II		20 ppm	
PROHIBIDOS / FORBIDDEN					
Metales Pesados		Conforme/According Oeko-Tex II		Niquel 0,5 Pg/cm ² - Cadmio 75 pm - Plomo 100 ppm	
AZO Colorants		Conforme/According Oeko-Tex II		No detectable	
Colorantes Alérgicos		Conforme/According Oeko-Tex II		No detectable (LMBG) (1/4/96)	
SÍMBOLOS DE LAVADO / WASH CARE SYMBOLS					
Observaciones: TRAS 25 LAVADOS EL ACABADO EMPIEZA A PERDER PROPIEDADES - LAVAR CON DETERGENTE NEUTRO <i>AFTER 25 WASHES THE FINISH BEGINS TO LOSE PROPERTIES - WASH WITH NEUTRAL DETERGENT</i> NO USAR LEJIA / DO NOT USE BLEACHING PLANCHADO A 140° de 10-15 SEGUNDOS / IRON 140° FOR 10-15 SECONDS GRS POST CONSUME bajo pedido / on request					